

# Introduction

- TMP Geocell is engineered for soil stabilization applications, it is used to help improve the performance of standard construction materials and erosion-control treatments.
- TMP Geocell is a lightweight and flexible three-dimensional, expandable panels made from high-density polyethylene(HDPE) strips which are ultrasonically bonded together to form an extremely strong configuration. TMP Geocell System can be filled with a wide range of material: aggregate, concrete, sand, soil, etc.

# Applications

- Erosion Control
- Load Support
- Slope Protection
- Channel Protection
- Retaining Wall
- Ground Stabilization
- Slope Protection Applications

#### Specifications

Index Properties	Test Method	Units	Values
■ Polymer	-	-	HDPE
Carbon Black content	ASTM D 1603	%	≥1.5
Density	ASTM D 1505	g/cm³	≥0.94
Sheet Thickness	ASTM D 5199	mm	1.10
Seam Peel Strength	-	Ν	1060
Weld Spacing	-	mm	400
■ Cell Depth	-	mm	75
Dimensions			
Expanded Cell Size (width $ imes$ length)	-	mm	295 X 250
<b>Expanded Panel Size (width</b> $ imes$ <b>length)</b>	-	m	4 X 5
Expanded Panel Area	-	m²	20 ±1%





# Introduction

- TMP Geocell is engineered for soil stabilization applications, it is used to help improve the performance of standard construction materials and erosion-control treatments.
- TMP Geocell is a lightweight and flexible three-dimensional, expandable panels made from high-density polyethylene(HDPE) strips which are ultrasonically bonded together to form an extremely strong configuration. TMP Geocell System can be filled with a wide range of material: aggregate, concrete, sand, soil, etc.

# Applications

- Erosion Control
- Load Support
- Slope Protection
- Channel Protection
- Retaining Wall
- Ground Stabilization
- Slope Protection Applications

#### Specifications

Index Properties	Test Method	Units	Values
■ Polymer	-	-	HDPE
Carbon Black content	ASTM D 1603	%	≥1.5
Density	ASTM D 1505	g/cm <sup>3</sup>	≥0.94
Sheet Thickness	ASTM D 5199	mm	1.10
Seam Peel Strength	-	Ν	1420
Weld Spacing	-	mm	400
■ Cell Depth	-	mm	100
Dimensions			
<b>Expanded Cell Size (width</b> $ imes$ <b>length)</b>	-	mm	295 X 250
<b>Expanded Panel Size (width</b> $ imes$ length)	-	m	4 X 5
Expanded Panel Area	-	m <sup>2</sup>	$20\ \pm1\%$





### Introduction

- TMP Geocell is engineered for soil stabilization applications, it is used to help improve the performance of standard construction materials and erosion-control treatments.
- TMP Geocell is a lightweight and flexible three-dimensional, expandable panels made from high-density polyethylene(HDPE) strips which are ultrasonically bonded together to form an extremely strong configuration. TMP Geocell System can be filled with a wide range of material: aggregate, concrete, sand, soil, etc.

### Applications

- Erosion Control
- Load Support
- Slope Protection
- Channel Protection
- Retaining Wall
- Ground Stabilization
- Slope Protection Applications

#### Specifications

Index Properties	Test Method	Units	Values
Polymer	-	-	HDPE
Carbon Black content	ASTM D 1603	%	≥1.5
Density	ASTM D 1505	g/cm³	≥0.94
Sheet Thickness	ASTM D 5199	mm	1.10
Seam Peel Strength	-	Ν	2130
Weld Spacing	-	mm	400
■ Cell Depth	-	mm	150
Dimensions			
<b>Expanded Cell Size (width</b> $ imes$ <b>length)</b>	-	mm	295 X 250
<b>Expanded Panel Size (width</b> $ imes$ <b>length)</b>	-	m	4 X 5
Expanded Panel Area	-	m²	20 ±1%





# Introduction

- TMP Geocell is engineered for soil stabilization applications, it is used to help improve the performance of standard construction materials and erosion-control treatments.
- TMP Geocell is a lightweight and flexible three-dimensional, expandable panels made from high-density polyethylene(HDPE) strips which are ultrasonically bonded together to form an extremely strong configuration. TMP Geocell System can be filled with a wide range of material: aggregate, concrete, sand, soil, etc.

### Applications

- Erosion Control
- Load Support
- Slope Protection
- Channel Protection
- Retaining Wall
- Ground Stabilization
- Slope Protection Applications

#### Specifications

Index Properties	Test Method	Units	Values
Polymer	-	-	HDPE
Carbon Black content	ASTM D 1603	%	≥1.5
Density	ASTM D 1505	g/cm³	≥0.94
Sheet Thickness	ASTM D 5199	mm	1.10
Seam Peel Strength	-	Ν	2840
Weld Spacing	-	mm	400
■ Cell Depth	-	mm	200
Dimensions			
<b>Expanded Cell Size (width</b> $ imes$ <b>length)</b>	-	mm	295 X 250
<b>Expanded Panel Size (width</b> $ imes$ <b>length)</b>	-	m	4 X 5
Expanded Panel Area	-	m²	20 ±1%

